

PROCEDURE

- A. Wash area with clean water to remove dust and dirt.
- B. Dry the panel.
- BRUSH* → C. Apply paint remover. *Remove with brush*
- D. After sufficient time has passed, removed with lacquer thinner.
- E. Be careful not to allow any of the removing materials to touch adjacent panels. *Wash with water*

From this point on the procedure will be the same as for newer trailers.

For new uncoated metal, wash with lacquer thinner, mask and spray.

Material is normally thinned no more than one quart thinner to the gallon. Can be used unthinned.